

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
22 January 2004 (22.01.2004)

PCT

(10) International Publication Number
WO 2004/008540 A1

(51) International Patent Classification⁷: **H01L 27/146,**
31/105

PRIMA, Jens [DE/DE]; Wiesenweg 9, 49596 Gehrde
(DE). **MIRHAMED, Arash** [DE/DE]; Steintuecker Weg
2, 34246 Vellmar (DE).

(21) International Application Number:
PCT/EP2003/007593

(74) Agent: **ADLER, Peter**; Lippert, Stachow, Schmidt & Partner,
Krenkelstrasse 3, 01309 Dresden (DE).

(22) International Filing Date: 14 July 2003 (14.07.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
102 32 019.5 16 July 2002 (16.07.2002) DE

(71) Applicant (for all designated States except US): **STMICROELECTRONICS NV** [NL/NL]; WTC Schiphol Airport,
Schiphol Boulevard 265, NL-NL-1118BH Schiphol Airport Amsterdam (NL).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and


(75) Inventors/Applicants (for US only): **RIEVE, Peter** [DE/DE]; Hauptstrasse 142, 51570 Windeck-Dattenfeld (DE). **WALDER, Marcus** [DE/DE]; Schwickertshausen 2, 51688 Wipperfurth (DE). **SEIBEL, Konstantin** [DE/DE]; Frankfurter Strasse 102, 57074 Siegen (DE).

Published:

— with international search report

[Continued on next page]

(54) Title: TFA IMAGE SENSOR WITH STABILITY-OPTIMIZED PHOTODIODE



(57) Abstract: The invention relates to a TFA image sensor with stability-optimized photodiode for converting electromagnetic radiation into an intensity-dependent photocurrent with an intermetal dielectric, on which, in the region of the pixel matrix, a lower barrier layer (metal 2) is situated and a conductive layer (metal 2) is situated on said barrier layer, and vias being provided for the contact connection to the ASIC, said vias in metal contacts on the ASIC. The invention is based on the object of providing a TFA image sensor having improved electrical properties. This is achieved in that an intrinsic absorption layer (i) is provided between the TCO layer and the barrier layer (metal 2) with a layer thickness of between 300 nm and 600 nm. Before the application of the photodiodes, the topmost, comparatively thick metal layer of the ASIC is removed and replaced by a matrix of thin metal electrodes which form the back electrodes of the photodiodes, said matrix being patterned in the pixel raster.

TFA image sensor with stability-optimized photodiode

The present patent application relates to a TFA image
5 sensor with stability-optimized photodiode for
converting electromagnetic radiation into an intensity-
dependent photocurrent with an intermetal dielectric,
on which, in the region of the pixel matrix, a lower
10 barrier layer (metal 2) is situated and a conductive
layer (metal 2) is situated on said barrier layer, and
vias being provided for the contact connection to the
ASIC, said vias in metal contacts on the ASIC.

Such a TFA sensor (Thin Film on ASIC (TFA) Technology)
15 comprises a matrix-organized or linear arrangement of
pixels. The electronic circuits for operating the
sensor (e.g. pixel electronics, peripheral electronics,
system electronics) are usually realized using
CMOS-based silicon technology and form an application
20 specific integrated circuit (ASIC).

Isolated therefrom by an insulating layer and connected
thereto by means of corresponding electrical contacts,
there is situated on the ASIC a multilayer arrangement
25 as photodiode, which performs the conversion of
electromagnetic radiation into an intensity-dependent
photocurrent. Said photocurrent is transferred at
specific contacts - present in each pixel - of the
pixel electronics underneath (B. Schneider, P. Rieve,
30 M. Böhm, Image Sensors in TFA (Thin Film on ASIC)
Technology, ed. B. Jähne, H. Hausecker, P. Geißler,
Handbook of Computer Vision and Applications,
pp. 237-270, Academic Press, San Diego, 1999).

35 According to the prior art (J.A. Theil, M. Cao,
G. Kooi, G. W. Ray, W. Greene, J. Lin, A.J. Budrys,
U. Yoon, S. M a, H. Stork, Hydrogenated Amorphous
Silicon Photodiode Technology for Advanced CMOS Active
Pixel Sensor Imagers, MRS Symposium Proceedings,

vol. 609, 2000), what is used as photodiode is a pin configuration based on amorphous silicon, i.e. a sequence comprising a p-conducting, an intrinsically
5 conducting (intrinsic) and an n-conducting amorphous silicon layer. The n-type layer usually forms the bottom most layer facing the ASIC.

The electrical contacts are formed by a metal layer,
10 for example, on said side facing the ASIC, while the contact connection on the side facing the direction of light incidence is generally effected by a transparent and conductive layer.

15 Over and above the pin photodiode mentioned, further component structures are also possible, e.g. Schottky photodiodes, in which an intrinsic semiconductor layer is brought into contact with a suitable metal (for example chromium, titanium, platinum, palladium,
20 silver), so that the metal-semiconductor junction forms a Schottky photodiode.

A typical layer configuration is disclosed in the patent application TFA image sensor with extremely low
25 dark current (file reference 10063837.6). Furthermore, detector structures with a controllable spectral sensitivity are known (P. Rieve, M. Sommer, M. Wagner, K. Seibel, M. Böhm, a-Si:H Color Imagers and Colorimetry, Journal of Non-Crystalline Solids,
30 vol. 266-269, pp. 1168-1172, 2000). This basic structure of a TFA image sensor can furthermore be extended by additional, upstream layers in the direction of light incidence, for example by color filter layers (e.g. Bayer pattern, US patent
35 No. 3971065).

If amorphous silicon is used as photoactive sensor material, then the metastability observed in the case

of this material becomes apparent, under certain circumstances. Hydrogenated amorphous silicon (a-Si:H) comprises a silicon-hydrogen atomic composite lacking a long-range order as is typical of semiconductor crystals. Modifications of the atom bonding parameters occur with respect to the ideal semiconductor crystal. The consequence of this is that, in the context of the solid-state band model, a state density that differs from zero exists in the band gap between conduction band and valence band, which affects the electrical and optical properties of the material. States in the middle of the band gap predominantly act as recombination centers, while states in the vicinity of the band edges function as traps for charge carriers. On account of light being radiated in or injection of charge carriers, more precisely through recombination of injected charge carriers, weak silicon bonds are broken and additional band gap states arise.

These band gap states caused by light irradiation represent additional recombination or trapping centers and influence the charge carrier transport and the distribution of the electric field strength in the components fabricated from amorphous silicon. In pin photodiodes, for example, predominantly positively charged states are concentrated in traps in that region of the intrinsic layer (i-type layer) which adjoins the p-type layer, and negatively charged states in that region of the i-type layer which adjoins the n-type layer. These stationary charges result in a decrease in the magnitude of the electric field strength within the i-type layer, so that the accumulation of photogenerated charge carriers deteriorates. An efficient charge carrier accumulation in pin photodiodes made of amorphous silicon is provided when the drift length ($\mu\tau E$) of the charge carriers significantly exceeds the thickness d of the intrinsic

layer:

$$\mu\tau E \gg d$$

(1)

- 5 On account of the increase in the defect density associated with light being radiated in, on the one hand the lifetime τ is reduced due to intensified recombination of charge carriers and on the other hand the electric field E is reduced on account of the
- 10 charged states in the i-type layer. Both have the consequence that the ratio of drift length to i-type layer thickness is reduced and the photocurrent thus decreases. The decrease in the photocurrent becomes apparent particularly when the photodiode is operated
- 15 near the short-circuit point without additional reverse voltage, i.e. when only the built-in potential difference brought about by the doped layers is effective.
- 20 When reverse voltage is applied, by contrast, the electric field intensifies, so that the charge carrier accumulation is impaired to a less extent. The essential consequence of the light irradiation of a photodiode made of amorphous silicon with regard to the
- 25 photocurrent thus consists in a reduction of the photocurrent saturation.

The dark current of an a-Si:H photodiode, i.e. the current which flows even in the unilluminated state is

30 likewise influenced by the degradation of the material. On account of the defect states additionally generated by light being radiated in, the thermal generation of charge carriers increases in the case of a reverse-biased photodiode (extraction), which is manifested in

35 an increase in the dark current.

The invention is now based on the object of providing a TFA image sensor with stability-optimized photodiode

for converting electromagnetic radiation into an intensity-dependent photocurrent having improved electrical properties.

5

The formulated object on which the invention is based is achieved, in the case of a TFA image sensor with stability-optimized photodiode for converting electromagnetic radiation into an intensity-dependent photocurrent, in that a layer thickness of the intrinsic absorption layer of between 300 nm and 600 nm is provided.

Further refinements of the invention emerge from the associated subclaims.

The object on which the invention is based is furthermore achieved by means of a method which is characterized in that, before the application of the photodiodes, the topmost, comparatively thick metal layer of the ASIC is removed and replaced by a matrix of thin metal electrodes which form the back electrodes of the photodiodes, said matrix being patterned in the pixel raster.

25

Further refinements of the method according to the invention emerge from the associated subclaims.

One particular refinement of the invention is characterized by opening of the ASIC passivation in the photoactive region of the TFA sensor, removal of the antireflection layer of the upper metalization layer of the ASIC in the photoactive region of the TFA sensor, removal of the conductive layer of the upper metalization layer of the ASIC in the photoactive region of the TFA sensor, patterning or removal of the lower barrier layer of the upper metalization layer of the ASIC in the photoactive region of the TFA sensor,

deposition and patterning of a further metal layer,
deposition and patterning of the photodiode layers, and
deposition and patterning of further layers, such as
5 color filter layers.

The changes in the dark current and photocurrent
brought about by light being radiated in are reduced,
according to the invention, by reducing the thickness
10 of the intrinsic layer. This measure brings about an
increase in the electric field strength over the i-type
layer, so that the field strength depth caused by the
increase in the defect density on account of light
being radiated in, within the i-type layer, is less
15 sharply pronounced.

In this way, the accumulation condition for
photogenerated charge carriers which is given by
equation (1) can be met even in the state of increased
20 defect density (after light has been radiated in), and
a decrease in photosensitivity is avoided. With regard
to the behavior of the photodiode without illumination,
photodiodes with a small i-type layer thickness, in the
aged state, have a lower dark current than those with a
25 thick i-type layer, which can be attributed to the
smaller number of generation centers present in the
band gap.

The method of improving the stability of photodiodes
30 made of amorphous silicon by means of a thin absorber
layer is known from the field of photovoltaic
technology, where it is employed successfully in solar
cells based on amorphous silicon. Application to image
sensors in TFA technology is novel. The method is
35 suitable both for photodiodes of the pin or nip type
and for Schottky diodes. A layer thickness of the
intrinsic absorption layer of between 300 nm and 600 nm
has proved to be advantageous with regard to the

stability of the photodiode, and it should preferably be approximately 450 nm.

- 5 One advantageous development consists in increasing the band gap of the intrinsic absorber layer of the photodiode. The dark current can be reduced in this way. At the same time, it is possible to counteract the increase in the diode capacitance which accompanies the
10 reduction of the i-type layer thickness. Technologically, it is possible to increase the band gap for example by using an amorphous silicon-carbon alloy (a-SiC:H) as absorption layer.
- 15 In photodiodes with a small i-type layer thickness, the configuration of the surface on which the diode is situated is of crucial importance for the magnitude of the dark current. Besides the thermal generation currents already mentioned, inhomogeneities of the ASIC
20 surface form, caused by the structures (metal tracks, holes in passivation layer, etc.) situated thereon, a further source of undesirably high dark currents in TFA image sensors. In this case, the influence of the surface topography is greater, the thinner the
25 photodiode situated thereon. In this respect, it is necessary in particular to deposit the photodiode of reduced layer thickness on a surface that is as planar as possible.
- 30 One advantageous development of the invention thus consists in depositing the photodiode with small i-type layer thickness (as mentioned above) on an ASIC having a flat surface topography. This is ensured by the fabrication process explained below. The ASIC can, but
35 need not necessarily, be coated with a passivation.

Within the pixel matrix, firstly the back electrodes of all the pixels are connected to one another via the

topmost CMOS metal plane, which is made planar in the region of the pixel matrix. This metal area is situated on a CMP-planarized surface (CMP = Chemical Mechanical Polishing) of the topmost intermetal dielectric layer. Before the application of the photodiodes, this topmost, comparatively thick metal layer of the ASIC is removed and replaced by a matrix of thin metal electrodes which form the back electrodes of the photodiodes, said matrix being patterned in the pixel raster. The topmost metallization of the ASIC generally comprises a multilayered arrangement comprising a lower barrier layer, e.g. titanium nitride or titanium, the actual conductive layer, e.g. aluminum (alloys) and, if appropriate, an upper antireflection layer, e.g. titanium nitride. In an expedient manner, the antireflection layer (if present) and the metal layer are completely removed above the pixel matrix, so that all that remains is the lower barrier layer. The latter is then patterned in the pixel raster and either forms the pixel back electrode directly, or it is coated with a further metal layer, e.g. chromium, which forms the matrix of the pixel back electrodes after a further patterning step. As an alternative, the lower barrier layer is completely removed, this then being followed by the deposition and patterning of the further metal layer in the form of pixel back electrodes.

The process steps are summarized below as key points:

- a) if appropriate opening of the ASIC passivation in the photoactive region of the TFA sensor,
- b) if appropriate removal of the antireflection layer of the upper metallization layer of the ASIC in the photoactive region of the TFA sensor,
- c) removal of the conductive layer of the upper

metallization layer of the ASIC in the photoactive region of the TFA sensor,

- 5 d) patterning or removal of the lower barrier layer of the upper metallization layer of the ASIC in the photoactive region of the TFA sensor,
- e) if appropriate deposition and patterning of a
10 further metal layer,
- f) deposition and patterning of the photodiode layers,
- 15 g) if appropriate deposition and patterning of further layers (e.g. color filter layers).

In this way, a largely planar surface is ensured in the region of the active pixel matrix of the sensor because
20 the etching attack into the topmost intermetal dielectric layer is reduced to a minimum. It is only during the patterning or removal of the lower barrier layer of the topmost ASIC metallization layer that the CMP-planarized dielectric layer is uncovered and is
25 removed locally by the etching attack, which can be minimized by a suitable choice of process parameters. Apart from that, the flat surface topography of the CMP planarization is maintained, thus avoiding any influencing of the dark current of the photodiodes
30 deposited thereon.

The invention is explained below with reference to some drawings. Figures 1 and 2 show a pin and, respectively, a Schottky photodiode with an intrinsic absorption
35 layer i according to the invention made of amorphous silicon in the layer thickness range of between 300 nm and 600 nm. The following figures relate to the abovementioned fabrication process which ensures a

largely planar surface topography.

In this case, the illustrations only include the
5 topmost layers of the ASIC which are relevant to the
interface with the TFA layers.

Figure 3 illustrates the initial state before the
beginning of the TFA processing in the form of a
10 passivated ASIC with passivation that has been opened
in the region of the pixel matrix. The antireflection
layer of the topmost metallization layer of the ASIC is
likewise removed in the pixel region.

15 In this case, firstly an intermetal dielectric is
arranged on the ASIC and, in the region of the pixel
matrix, a lower barrier layer (metal 2) is situated on
said intermetal dielectric and a conductive layer
(metal 2) is situated on said barrier layer. Vias are
20 provided for the contact connection to the ASIC, said
vias ending in metal contacts on the ASIC. Furthermore,
a bond pad (metal 2) for external contact connection is
provided, which is contact-connected to the ASIC by
means of vias and a metal 1.

25

The state after the removal of the conductive layer of
the topmost metallization is recorded in Figure 4.

Figure 5 documents the result after the patterning of
30 the lower barrier layer. This produces the pixel back
electrodes, which are subsequently coated with the
multilayer system comprising amorphous silicon and TCO
(Figure 6). Figures 7 and 8 show a process variant in
which, proceeding from the situation according to
35 Figure 5, the patterned regions of the lower barrier
layer are covered by a further patterned metal layer
before the deposition of the photodiode. Beginning with
Figure 9, a further variant is illustrated in which,

after the situation outlined in Figure 4, the lower barrier layer of the topmost metallization layer of the ASIC is completely removed. The further metal layer is
5 subsequently deposited directly onto the intermetal dielectric, and forms the pixel back electrodes after patterning (Figure 10). The photodiode-forming layers are then applied thereto (Figure 11).

TFA image sensor with stability-optimized photodiodes**Patent Claims**

5

1. A TFA image sensor with stability-optimized photodiode for converting electromagnetic radiation into an intensity-dependent photocurrent with an intermetal dielectric, on which, in the region of the pixel matrix, a lower barrier layer (metal 2) is situated and a conductive layer (metal 2) is situated on said barrier layer, and vias being provided for the contact connection to the ASIC, said vias ending in metal contacts on the ASIC, **characterized** in that an intrinsic absorption layer (i) is provided between the TCO layer and the barrier layer (metal 2) with a layer thickness of between 300 nm and 600 nm.

2. The TFA image sensor as claimed in claim 1, **characterized** in that the layer thickness of the intrinsic absorption layer (i) is approximately 450 nm.

3. The TFA image sensor as claimed in claims 1 and 2, **characterized** in that the band gap of the intrinsic absorption layer (i) of the photodiode is increased.

4. The TFA image sensor as claimed in one of claims 1 to 3, **characterized** in that the increase in the band gap is realized by using an amorphous silicon-carbon alloy (a-SiC:H) as absorption layer.

5. The TFA image sensor as claimed in one of claims 4, **characterized** in that, in particular, the photodiode of reduced layer thickness is arranged on a surface that is as planar as possible.

6. The TFA image sensor as claimed in one of claims 1 to 5, **characterized** in that the photodiode with small

intrinsic layer thickness is deposited on an ASIC having a flat surface topography.

5 7. The TFA image sensor as claimed in one of claims 1 to 6, **characterized** in that the ASIC is coated with a passivation.

10 8. The TFA image sensor as claimed in one of claims 1 to 7, **characterized** in that, within the pixel matrix, firstly the back electrodes of all the pixels are connected to one another via the topmost CMOS metal plane, which is made planar in the region of the pixel matrix.

15 9. The TFA image sensor as claimed in claim 8, **characterized** in that the metal plane is situated on a CMP-planarized surface (CMP = Chemical Mechanical Polishing) of the topmost intermetal dielectric layer.

20 10. A method for fabricating a TFA image sensor as claimed in one of claims 1 to 9, **characterized** in that, before the application of the photodiodes, the topmost, comparatively thick metal layer of the ASIC is removed and replaced by a matrix of thin metal electrodes which
25 form the back electrodes of the photodiodes, said matrix being patterned in the pixel raster.

30 11. The method as claimed in claim 10, **characterized** in that an antireflection layer that is present and the metal layer are completely removed above the pixel matrix, so that all that remains is the barrier layer situated underneath.

35 12. The method as claimed in claim 10, **characterized** in that the lower barrier layer is completely removed, this then being followed by the deposition and patterning of the further metal layer in the form of

pixel back electrodes.

13. The method as claimed in one of claims 10 to 12,
characterized in that the ASIC passivation is opened in
5 the photoactive region of the TFA sensor.

14. The method as claimed in one of claims 10 to 13,
characterized by the removal of the antireflection
layer of the upper metalization layer of the ASIC in
10 the photoactive region of the TFA sensor.

15. The method as claimed in one of claims 10 to 14,
characterized by the removal of the conductive layer of
the upper metalization layer of the ASIC in the
15 photoactive region of the TFA sensor.

16. The method as claimed in one of claims 10 to 15,
characterized by patterning or removal of the lower
barrier layer of the upper metalization layer of the
20 ASIC in the photoactive region of the TFA sensor.

17. The method as claimed in one of claims 10 to 16,
characterized by deposition and patterning of a further
metal layer.

25

18. The method as claimed in one of claims 10 to 17,
characterized by deposition and patterning of further
layers, such as color filter layers.

30 19. A method for fabricating a TFA image sensor as
claimed in one of claims 1 to 9, characterized by

- opening of the ASIC passivation in the photoactive
region of the TFA sensor,

35

- removal of the antireflection layer of the upper
metalization layer of the ASIC in the photoactive
region of the TFA sensor,

- removal of the conductive layer of the upper metalization layer of the ASIC in the photoactive region of the TFA sensor,
- 5
- patterning or removal of the lower barrier layer of the upper metalization layer of the ASIC in the photoactive region of the TFA sensor,
- 10
- deposition and patterning of a further metal layer,
 - deposition and patterning of the photodiode layers, and
- 15
- deposition and patterning of further layers, such as color filter layers.

Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11

